

Table D.6 — Conversion between various Vickers hardness scales for high speed steels of steel grade X79WCo18.5

X79WCo18.5高速钢的不同维氏硬度单位换算值

HV	HV 10	HV 5
790	795	794
800	806	805
810	817	816
820	828	826
830	839	837
840	850	847
850	861	858
860	872	868
870	883	879
880	894	890
890	905	900
900	916	911
910	927	921
920	938	932

NOTE If only HV is given without a number, then most probably HV30 is meant.